



1100 SERIES ATHLETIC PLASTISOL INK



RECOMMENDED FABRICS
Nylon mesh
100% Cotton
Some 50/50 Cotton/Polyester Blends



INK APPLICATION
1100 Series Athletic Ink can be printed directly from the container. If printing on Nylon substrates, it should be mixed with the 900 Catalyst before printing, for adhesion.



ADDITIVES
If modification is necessary, use 1% to 5% by weight of 1110 Curable Reducer.



SCREEN MESH
60-160 t/in (24-63 t/cm)
monofilament



EMULSION
Any direct or indirect emulsion or capillary film in the 35 to 70 micron range



SQUEEGEE
70-80 Durometer
Sharp edge



CURE TEMPERATURES
325°F (163°C) entire ink film



CLEAN-UP
Any eco-friendly plastisol screen wash



PRODUCT PACKAGING
Quart, 1 gallon, 5 gallon, 30 gallon or 50 gallon containers



STORAGE OF INK CONTAINERS
65° to 90°F (18°C to 32°C)
Avoid storage in direct sunlight
Keep containers well sealed



SDS
Refer to SDS prior to use

FEATURES

1100 Series Athletic Plastisol Ink is a very durable, high viscosity plastisol ink formulated for printing directly onto most athletic garments.

Can also be used for cold peel transfers and as a flock adhesive.

It can also be used with 900 Catalyst for greater durability and adhesion on problem fabrics.

COLORS

- 1113 Athletic White
- 1116 Athletic Black
- 900 Catalyst **

** Catalyst must be ordered separately

INK APPLICATION

The 1100 Series Athletic Plastisol Inks can be printed directly from the container or for greater durability and adhesion on problem fabrics (micro-mesh), mix with the 900 Catalyst. In general, if the ink can surround the fiber of the fabric being printed, the use of 900 Catalyst may not be necessary. Catalyst must be purchased separately if needed. 900 Catalyst is available in 2 oz. and 8 oz. containers and when used should be thoroughly hand stirred into the ink to the following proportions:

- By volume = 16 parts ink to 1 part catalyst
- By weight = 20 parts ink to 1 part catalyst

- 1 ounce of catalyst to 1 pint of ink
- 2 ounces of catalyst to 1 quart of ink
- 8 ounces of catalyst to 1 gallon of ink

Ink may be used immediately after mixing. Do not mix more ink than is needed for a job. Do not under-catalyze the ink. Pot life of mixed ink is 4 to 8 hours. Over-catalyzation will shorten the pot life.

If printing on cotton, it is not necessary to catalyze the ink. Print it as you would a normal direct print plastisol ink.

For standard cotton, recommended screen mesh is 110-160 t/in (43-63 t/cm). For coarse athletic fabrics (mesh football jerseys), recommended screen mesh is 4XX to 6XX.

IMPORTANT INFORMATION

Adding too much reducer or other additives to the 1100 Series inks may cause curing/fusing or increased dye migration problems. It is important not to use reducers that are 100% plasticizer, because they may decrease adhesion and make the finished ink film less durable. Test dryer temperatures and wash test printed product before and during a production run.

LEGAL DISCLAIMER

Recommendations and statements made are based on International Coatings' research and experience. Since International Coatings does not have any control over the conditions of use or storage of the product sold, International Coatings cannot guarantee the results obtained through use of its products. All products are sold and samples given without any representation of warranty, expressed or implied, of fitness for any particular purpose or otherwise, and upon condition that the buyer shall determine the suitability of the product for its own purpose. This applies also where rights of third parties are involved. It does not release the user from the obligation to test the suitability of the product for the intended purpose and application.

REV. 1600003

